



A&P Technology

BIAXIAL BRAIDED SLEEVINGS OFFERING:

- Ease of Layup
- Conformability and Repeatability
- Fiber Continuity Providing Superior Impact Performance and Better Fatigue Performance

J81L50X Technical Data Sheet

SLEEVING: 2 x 2 Twill

RAW MATERIAL: Kevlar 49 1420 Denier

[LINK TO KEVLAR FIBER DATASHEET](#)

SLEEVING DIAMETER: .50" (12.7 mm)

BRAID ANGLE: +/-45°

BRAID YIELD: 166.7 ft/lb (112 m/kg)

AREAL WEIGHT: 224 GSM

LAYER THICKNESS: (@50%FV): .012" (.30 mm)

STANDARD SLEEVING TOLERANCES YIELD

TOLERANCE: +/-10%

ANGLE TOLERANCE: +/-3°



Better With Braid.®

For more information, please visit www.braider.com OR contact a sales rep at sales@braider.com or 513-688-3200