

ASP Technology

BIAXIAL BRAIDED SLEEVINGS OFFERING:

- Ease of Layup
- Conformability and Repeatability
- Fiber Continuity Providing Superior Impact Performance and Better Fatigue Performance

T26L125X Technical Data Sheet

SLEEVING: 2 x 2 Twill **RAW MATERIAL:** 1800 Roving Fiberglass

SLEEVING DIAMETER: 1.25" (31.8 mm) BRAID ANGLE: +/-45° BRAID YIELD: 39.8 ft/lb (27 m/kg) AREAL WEIGHT: 376 GSM LAYER THICKNESS: (@50%FV): .012" (.30 mm)

STANDARD SLEEVING TOLERANCES YIELD TOLERANCE: +/-10% ANGLE TOLERANCE: +/-3°



Better With Braid.

For more information, please visit www.braider.com OR contact a sales rep at sales@braider.com or 513-688-3200

All technical information and data contained herein is believed accurate and reliable. However, the accuracy and completeness of this information is not guaranteed and is subject to change without notice. A&P Technology shall not be liable for injury, loss or damage whether direct or consequential arising out of use of the data provided herein.