

## ASP Technology

## **BIAXIAL BRAIDED SLEEVINGS OFFERING:**

- Ease of Layup
- Conformability and Repeatability
- Fiber Continuity Providing Superior Impact Performance and Better Fatigue Performance

## T22L56L200X Technical Data Sheet

**SLEEVING:** 2 x 2 Twill

RAW MATERIAL: G34-700 12K Carbon (MCGC) LINK TO

**CARBON FIBER DATASHEET** 

RAW MATERIAL: 450 Roving Fiberglass

**SLEEVING DIAMETER:** 2.0" (50.8 mm)

**BRAID ANGLE:** +/-45°

**BRAID YIELD:** 11.5 ft/lb (7.7 m/kg)

**AREAL WEIGHT: 810 GSM** 

**LAYER THICKNESS:** (@50%FV): .029" (.75 mm)

STANDARD SLEEVING TOLERANCES YIELD

**TOLERANCE:** +/-10%

ANGLE TOLERANCE: +/-3°



## Better With Braid.

For more information, please visit www.braider.com OR contact a sales rep at sales@braider.com or 513-688-3200